




## Williamsburg #3


Non-carbonated slate formed by tectonic compression. Blue black slate with non rusting metallic particles and thin laminations.



Quarry Solana de Forcadas. San Pedro de Trones (Leon) Spain.

Operating since 1892.

Sizes: 25x15 - 50x45 cm  
Thickness: 3.5 - 5 - 7.65 mm



### Formats



Rectangular

Bullnose

Innova

### Selections



### Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO, EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
0,22% Code: WI (< 0,4%)	0,50% Complies (< 1,5%)	Longitudinal 45,4 MPA Transverse 50 MPA	S1	T1	Fulfill < 0,6%

### International certifications



European Standard: EN 12326 | French Specifications: NF 02/01 N° 5273 | Belgian Specifications: ATG H571 | American Standard: ASTM C406-15 | Bre Specification: BREG EN EPD000246